# resimac Ltd.

# 208 CERAMIC UW

**Resimac 208 Ceramic UW** is a flexible high build solvent-free epoxy coating designed for application to wet or underwater surfaces. The ceramic enhanced product provides long term protection of steel and concrete structures against corrosion, abrasion and chemical attack. The product cures at 5°C (41°F)and is applied in a single coat at 750 microns to 1mm (40mil) thickness

### **Typical applications**

Subsea structures, pipelines, risers, splash zones, sheet and bearing piles, other land and marine structures

# **Characteristics**

#### Appearance

Base: Dark Grey Activator: Amber liquid Mixed: Dark Grey liquid

#### Mixing Ratio

By weight: 5.6:1 By volume: 4:1

#### Density

Base:	1.40
Activator:	0.99
Mixed:	1.32

Volume Capacity 649cc/Kg

# Solids content

Sag Resistance

Nil at 1000 microns

#### Coverage

4ltr (1.05 US gallons) of fully mixed product will give the following coverage rates – 5.333m<sup>2</sup> at 750 microns 57.28ft<sup>2</sup> at 30mil

4m<sup>2</sup> at 1000 microns

43ft<sup>2</sup> at 40mil Please note that the coverage rates quoted are theoretical and do not take into consideration the profile or condition of the surface being repaired.

#### **Cure Times**

The applied material should be allowed to harden for the times indicated below before being subjected to the conditions indicated:

#### Usable life

10°C	90 minutes
20°C	45 minutes
30°C	22.5 minutes
40°C	11 minutes

#### Touch dry

-	
10°C	12 hours
20°C	6 hours
30°C	3 hours
40°C	1.5 hours

#### Hard dry

10°C	24 hours
20°C	12 hours
30°C	6 hours
40°C	3 hours

#### Full Cure

 10°C
 6 days

 20°C
 3 days

 30°C
 1.5 days

 40°C
 18 hours

#### Storage life

5 years if unopened and stored in normal dry conditions (15-30°C)

## Mechanical Properties

Abrasion Resistance Taber CS17 Wheels/1 Kg load 38mm<sup>3</sup> loss/1000 cycles

#### Adhesion

**Tensile Shear** to ASTM D1002 on abrasive blasted dry mild steel with 75 micron profile 184kg/ cm<sup>2</sup> (2610psi) **Tensile Shear** to ASTM D1002 on abrasive blasted wet mild steel with 75 micron profile 176kg/ cm<sup>2</sup> (2500psi)

#### **Corrosion Resistance**

Tested to ASTM B117 Minimum 1000 hours

#### Flexural Strength

Tested to ASTM D790 614kg/cm<sup>2</sup> (8710psi)

#### Impact Resistance

Tested to ASTM D256 32J/m

#### Hardness

Shore D to ASTM D2240 20°C 80

#### Approvals

Approved by BUREAU VERITAS for Surface Protection and Cold Repair Products applied to Marine Vessels. Certificate No: 55258/AO BV Expiry: 24<sup>th</sup> March 2024



#### **Chemical Resistance**

The product resists attack by a wide variety of inorganic acids, alkalies, salts and organic media.

For more detailed information refer to the Resimac Technical Centre for advice.

#### Quality

All Resimac Products are supplied under the scope of the company's fully documented quality system.

#### Warranty

Resimac warrants that the performance of the product supplied will conform to the typical descriptions quoted within this specification provided material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

#### Health and safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves and other recommended personal protective equipment must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read and fully understood the detailed Material Safety Data Sheet

Legal Notice: The data contained within this Product Specification is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.

Resimac Ltd, Unit B, Park Barn Estate, Station Road, Topcliffe, Thirsk, YO7 3SE, United Kingdom Tel: +44 1845 577498 Web: www.resimacsolutions.com Email: info@resimac.co.uk PSS208UW.rv6.21062022